



PRODUCT SPECIFICATION NONWOVEN

Item	17 gr/m2
Fibres (DIN 60001)	100% Polypropylene
Nonwoven Type (DIN 61210)	Spunbonded filaments
Bonding of the nonwoven (DIN 61210)	Thermobonded

Mass per unit area (EN 29073 T1)	g/m2	17	±3%
Thickness (DIN 53855)	mm	0.12	±10%
Max Tensile strength (EN 29073 T3) md	N/5 cm	28	±10%
Max Tensile strength (EN 29073 T3) cd	N/5 cm	26	±10%
Tear Strength (EN 29073 T4)	md N/5 cm	16	±10%
Tear Strength (EN 29073 T4)	cd N/5 cm	14	±10%

UV stabilisation 1 season Southern Europe conditions.

Average of 15 individual values.